Rua Maximiliano Gaidzinski 245 88845-000 Cocal do Sul - SC - Brasil Tel + 55 48 3447 7981 Fax + 55 48 3447 7706 www.eliane.com



TECHNICAL CHARACTERISTICS OF PRODUCT

The characteristics of the product specified in this technical report meet the specification and test methods according to norm ASTM requirements.

PRODUCT SPECIFICATION

Reference	ELEMENT GRAY AC 30X60
Product Code	8029383
Nomimal Size (N)	30 cm x 60 cm
Work Size (W)	300,0 mm x 600,0 mm
Thickness	9,0 mm
Water Absorption	Bla (≤0,50%)
Shade Variation	V2
Application Joint	3,0 mm
Coverage Area	1,26 m ² /cx
Number of pieces per box	7
Usage Recommendation	LC

Check if the product is adequate for the planned installation area according to the room application table:

CODE	APPLICATION ROOM	
LA	Residendial bathrooms.	
LB	Residential areas, bedrooms and kitchens with no access to the street and LA spaces.	
LC	Commercial areas without access to the street, garages, porches and residential areas with access to the street, and LB and LA spaces.	
LD	Commercial areas with access to the street and LA, LB, and LA spaces.	
LE	Sidewalks and outside flat areas and LD, LC, LB and LA spaces.	
LP	Pools.	
LF	Façades.	

PHYSICAL PROPERTIES

Breaking strength (lbf)	≥ 250
Water Absorption (%)	≤ 0,5
Visible abrasion Resistance	IV

Eliane S/A Revestimentos Cerâmicos

Rua Maximiliano Gaidzinski 245 88845-000 Cocal do Sul - SC - Brasil Tel + 55 48 3447 7981 Fax + 55 48 3447 7706 www.eliane.com



DYNAMIC COEFFICIENT OF FRICTION

Dynamic coefficient of friction: Wet: 0,50

Test method according to norm ANSI A 137.

CHEMICAL PROPERTIES

Chemical Resistance Class B

Stain Resistance Class A

Attention:

- Sand may produce scratches on any type of surface covering (stone, wood, vinyl or ceramic tiles).
 Therefore, ceramic tiles are not warranted against scratches, especially concerning glossy surface products.
- Special care is recommended during the application and its use
- In residential areas, we recommend to protect the base of furniture and appliances.
- Product manufactured by the wet process.
- Product with Class I combustibility, according to NBR 15575

February 01, 2017. Cocal do Sul – SC – Brazil

Sergio Pereira Ruzza Gerente de Tecnologia Cerâmica Angela Waterkemper Vieira Analista Desenvolvimento de Processos